

PRODUCT DATA SHEET

PROPERTY	TEST	TYPICAL RESULTS	MEASURE UNIT
Density	DIN ISO 1183	1.85 – 1.90	g/cm ³
Impact Resistance (falling ball)	UNI EN 438-2:2005	>120	cm
Hardness (Barcol)	UNI EN4278	35 – 40	--
Resistance to Bacteria and Fungi		No development of bacteria and fungi population	n° di colonie
Degree of whiteness		>93	ΔL (CIE-Lab)
Stability under light exposure (Xenon)	UNI EN 9427/89	5	Range 1 - 5
Resistance to temperature changes	EN 14688	>1000	cycles
Stain Resistance	EN 14688	No defect	